

Abrasion Resistance Test Results: Comparison of Mühlen Sohn Fluitex® and Albany

Below you can find the abrasion test results of Mühlen Sohn Fluitex® and Albany woven material.
 The big difference is caused by:

- | | |
|--|---|
| 1.) the difference in raw materials: | Mühlen Sohn uses endless Multifilament yarns
Albany uses staple fibre yarns |
| 2.) the difference in weaving structure: | Mühlen Sohn covers the weft yarn with the individual warp yarns
Albany does not cover the weft yarns |

